ANISOTROPIC CRITICAL FIELDS of MgB₂ SINGLE CRYSTALS *

Т. ДАНМ

Universität Tübingen, Institut für Theoretische Physik Auf der Morgenstelle 14, 72076 Tübingen, Germany

A.I. Posazhennikova

Laboratorium voor Vaste-Stoffusica en Magnetisme Katholieke Universiteit Leuven, 3001 Leuven, Belgium

AND K. MAKI

Max-Planck-Institute for Physics of Complex Systems Nöthnitzerstr. 38, 01187 Dresden, Germany

 and

Department of Physics and Astronomy, University of Southern California Los Angeles, CA 90089-0484, USA

(*Received July 10, 2002*)

The recently discovered superconductivity in MgB₂ has created the world sensation. In spite of the relatively high superconducting transition temperature $T_c = 39$ K, the superconductivity is understood in terms of rare two gap superconductor with energy gaps attached to the σ and π -band. However, this simple model cannot describe the temperature dependent anisotropy in H_{c2} or the temperature dependence of the anisotropic magnetic penetration depth. Here we propose a model with two anisotropic energy gaps with different shapes. Indeed the present model describes a number of peculiarities of MgB₂ which have been revealed only recently through single crystal MgB₂.

PACS numbers: 74.20.Rp, 74.25.Bt, 74.70.Ad

^{*} Presented at the International Conference on Strongly Correlated Electron Systems, (SCES 02), Cracow, Poland, July 10–13, 2002.

1. Introduction

The discovery of new superconductivity in MgB₂ took the world by surprise [1]. Early studies based on polycrystalline samples lead to a two gap model [2–4]. On the other hand the anisotropy in $H_{c2}(t, \Theta)$ suggested an anisotropic *s*-wave model [5–9]. Further it is clear that the simple two gap model cannot describe the strong temperature dependence of $\gamma(t) =$ $H_{c2}^{ab}(t)/H_{c2}^c(t)$ observed in single crystal MgB₂ [6,9]. For this we need an order parameter $\Delta(\vec{k})$ of oblate shape [9]. On the other hand, it is well known that $H_{c2}^{ab}(t)/H_{c2}^c(t) > 1$ and $H_{c1}^{ab}(t)/H_{c1}^c(t) > 1$ for single crystal experiments [10–12], which contradicts the Ginzburg–Landau phenomenology. Further, both magnetic penetration depth data and $H_{c1}^c(t)$ data suggested a prolate order parameter as in [7,8]. Indeed, an earlier STM study suggested a prolate order parameter as well [13].

Is the order parameter prolate or oblate? The answer is that we need both. We suggest, that the oblate order parameter is attached to the σ -band while the prolate order parameter to the π -band. In the following we shall describe salient features of single crystal MgB₂ within the present model.

2. Upper critical field

We just point out two features in the upper critical field which are outside of the Ginzburg–Landau phenomenology: (a) the strong temperature dependence of the anisotropy parameter $\gamma(t) = H_{c2}^{ab}(t)/H_{c2}^c(t)$ [9]; (b) the deviation from the effective mass model $H_{c2}(t, \Theta)/H_{c2}(t, 0) \neq (\cos^2 \Theta + \gamma \sin^2 \Theta)^{-1/2}$ [6].

For example $\Delta(\vec{k}) \sim 1/\sqrt{1+az^2}$, where $z = \cos\Theta$ and $a \sim 100$ can describe the temperature dependence of $\gamma(t)$, as has been shown in Ref. [9]. Also, by fitting the experimental data we obtained $v_a \simeq 2.7 \times 10^7$ cm/sec and $v_c/v_a \simeq 0.48$. We point out that these values are very consistent with the ones for the σ -band [2].

By fitting experimental data for $H_{c2}(\theta)$ [14] close to T_c we can deduce the ratio $v_c/v_a \simeq 0.73$, implying a = 10, for example. This result is greater than that estimated in our previous analysis of $H_{c2}(T)$ [9]. Next order correction in $(T - T_c)/T_c$ leads to the increase of the ratio v_c/v_a for the same values of the parameter a. In the future we are going to elaborate our study of the upper critical field behavior in MgB₂ by taking into account impurity scattering, what we believe will improve the agreement with experiment.

3. Lower critical field

From c-axis oriented films and single crystals, the superfluid density $\rho_{s,a}$ and the lower critical fields H_{c1}^c and H_{c1}^{ab} have been extracted reliably [11,12]. It is clear this time that we need a prolate order parameter to fit these data.

We choose $\Delta(\vec{k}) = 1/\sqrt{1-az^2}$ with $a \simeq 0.92 \sim 0.95$. These values give a good fit of penetration depth data [11]. The magnetic penetration depths are related to the lower critical fields via the formulas

$$H_{c1}^{c}(t) = \frac{\Phi_{0}}{2\pi\lambda_{a}^{2}(t)} \ln \frac{\lambda_{a}(t)}{\xi_{a}(t)}, \qquad (1)$$

$$H_{c1}^{ab}(t) = \frac{\Phi_0}{2\pi\lambda_a(t)\lambda_c(t)} \ln \sqrt{\frac{\lambda_a(t)\lambda_c(t)}{\xi_a(t)\xi_c(t)}},$$
(2)

where $\lambda_a(t)$ and $\lambda_c(t)$ are the magnetic penetration depth with the supercurrent in the *ab*-plane and in parallel to the *c*-axis, respectively. They are related to the superfluid density via $\rho_{s,a}(t) = \lambda_a^2(0)/\lambda_a^2(t)$ and $\rho_{s,c}(t) = \lambda_c^2(0)/\lambda_c^2(t)$. Taking a = 0.95, which fits $\rho_{s,a}(t)$ from Ref. [11], we calculate $\rho_{s,c}(t)$ and obtain the temperature dependences of H_{c1}^c and H_{c1}^{ab} from Eqs. (1) and (2), neglecting the temperature dependence of the logarithms. The result is shown in Fig. 1 along with the experimental results from Ref. [12]. From these fits we obtain $H_{c1}^c(0) = 24$ mT and $H_{c1}^{ab}(0) = 32$ mT. From this the ratio of the relevant Fermi velocities can be estimated as $H_{c1}^{ab}(0)/H_{c1}^c(0) \approx v_c/v_a = 1.3$. In other words, the corresponding Fermi surface is more isotropic and further $v_c > v_a$. This strongly suggests that the prolate order parameter we are considering has to be associated with the π -band.



Fig. 1. Temperature dependence of the lower critical fields H_{c1}^c (dashed line) and H_{c1}^{ab} (solid line) along with the corresponding experimental data from Ref. [12].

4. Syntheses

We have seen so far that we need two energy gaps of different shape in order to describe $H_{c2}(t, \Theta)$ and $H_{c1}(t, \Theta)$. The temperature dependence of $\gamma(t)$ indicates that an oblate order parameter $(\Delta(\vec{k}) = 1/\sqrt{1 + az^2})$ dominates the behavior at high magnetic field. Also we need $v_c/v_a = 0.48$. This suggests the cylindrical Fermi surface associated with the σ -band as the carrier of this order parameter. On the other hand, for $H_{c1}(t, \Theta)$ we need a prolate order parameter $(\Delta(\vec{k}) = 1/\sqrt{1 - az^2})$. Also, the anisotropy in $H_{c1}(t, \Theta)$ suggests the π -band as the carrier of this order parameter. In other words, if we assume that the high field properties are controlled by the oblate order parameter attached to the σ -band, while the low field properties are due to the prolate order parameter attached to the π -band, we have a consistent picture for superconductivity in MgB₂.

We believe that this picture will be crucial to understand also a variety of anomalies observed in the vortex state in MgB_2 .

We would like to thank M. Angst, F. Bouquet, S. Haas, A. Janossy, A. Junod, B.B. Jin and N. Klein for useful discussions on MgB₂.

REFERENCES

- [1] J. Nagamatsu *et al.*, *Nature* **410**, 63 (2001).
- [2] S.V. Shulga *et al.*, cond-mat/0103154.
- [3] J.M. An, W.E. Pickett, Phys. Rev. Lett. 86, 4366 (2001).
- [4] A.Y. Liu, I.I. Mazin, J. Kortus, *Phys. Rev. Lett.* 87, 087005 (2001).
- [5] O.F. de Lima *et al.*, *Phys. Rev.* **B64**, 144517 (2001).
- [6] M. Angst et al., Phys. Rev. Lett. 88, 167004 (2002).
- [7] Y. Chen, S. Haas, K. Maki, Curr. Appl. Phys. 1, 333 (2001).
- [8] S. Haa, K. Maki, *Phys. Rev.* B65, 020502(R) (2002).
- [9] A.I. Posazhennikova, T. Dahm, K. Maki, cond-mat/0204272, to appear in Europhys. Lett..
- [10] C. Buzea, T. Yamashita, Supercond. Sci. Technol. 14, R115 (2001).
- [11] B.B. Jin et al., cond-mat/0112350, to appear in Phys. Rev. B.
- [12] M. Xu et al., Appl. Phys. Lett. 79, 2779 (2001).
- [13] P. Seneor et al., Phys. Rev. B65, 012505 (2002).
- [14] Yu. Eltsev et al., Physica C, proceedings of ISS2001, Kobe, Japan, Sept. 24–26, 2001, in press.